

Material	Protective Properties	Colouring Properties	Brightening Properties
LM0	★★★★★★	★★★★★★	★★★★★★
LM2	★★	★	★
LM4	★★★	★★	★
LM5	★★★★★★	★★★★★★	★★★★★
LM6	★★	★	★
LM9	★★	★	★
LM12	★★	★★	★
LM13	★★	★	★
LM16	★★★★	★★	★
LM20	★★★★	★★	★
LM21	★★	★	★
LM22	★★★★	★★	★
LM24	★★	★★	★
LM25	★★★★	★★	★
LM26	★★	★	★
LM27	★★★★	★★	★
LM28	★	★	★
LM29	★	★	★
LM30	★	★	★
LM31	★★★★★★	★★★★★★	★★★
BS2L99	★★★★	★★	★
BSL119	★★★★	★★★★	★
BSL154	★★★★	★★★★	★
BSL155	★★★★	★★★★	★
BSL169	★★★★	★★	★
BSL173	★★★★	★★	★
BSL174	★★★★	★★	★
DTD716B	★★★★	★★	★
DTD722B	★★★★	★★	★
DTD727B	★★★★	★★	★
DTD735B	★★★★	★★	★
DTD5008B	★★★★★★	★★★★★★	★★★
DTD5018A	★★★★★★	★★	★

Excellent=★★★★★★ Good =★★★★★★ Good =★★★★ Fair=★★★ Unsuitable=★

★★ = Only suitable for Dark Colours

★★ = Anodising conditions me be carefully controlled for good results